CONTRAFLAM® STRUCTURE LITE 60


Fire resistant safety glass for interior application

CLASSIFICATION


PRODUCT FEATURES

= Integrity + Radiation reduction

Ability to withstand fire exposure without transmission of fire to the non-fire side as a result of the passage of flames or hot gases, thereby causing ignition of the non-fire exposed surface or materials adjacent. Also maintains radiated heat in front of the glazing below a specified level to provide for safer separation distances and escape ways.



Intumescent material*** Silicone Sealant***



TECHNICAL SPECIFICATIONS

Reaction to fire (EN 13501-1)	A2-s1, c
Production height (Standard/Maximum)	≤ 3210 :

Maximum Glass Size

Variable, subject to glass make-up, framing material or glazed element type. Refer to applicable fire test evidence, national certification and EXAP allowance. Consult with your Vetrotech representative.

Thickness tolerance +2/-1 mm Length tolerance ±2 mm

Impact resistance (EN 12600) 1 (B) 1 classification

UV stability (EN ISO 12543-4 point 6) In addition to the standard specifications: no formation of bubbles or yellowing after 2000 hours of exposure to radiation.

Edge quality outer pane Polished edge in conformance with EN 12150-1

Application Conditions Avoid prolonged exposure to extreme temperatures. Exterior applications must be supplied as an IGU with Low-E or Solar Control coating. For more information consult your Vetrotech representative or refer to "Quality Guideline, Application Conditions".

CE certificate No. of conformity $0336\text{-}CPD\text{-}5064C/ID\ No.*\ (you\ can\ obtain\ a\ DoP^{**}\ from\ your\ national\ sales\ office)\ -\ AoC\text{-}level\ 1$ Hazardous material contained None

Assembly According to the instruction guideline

Nominal thickness

Glass size per thickness	≤ 2300 x 3800 mm
Weight (max. 500 kg/pane)	46 kg/m ²
Sound reduction Rw (EN 140-3)	39 dB
Light transmission (EN 410)	84%

Light reflection pL (outside/inside) 8%/8% U value, W/m²K (EN 673) 4,9

g value Energy transmission τE

Energy reflection ρE (outside/inside)

20 mm

0,68 61%

7%/7%



ID No. = Identification number for the relevant manufacturing site